

DPM Epoxy Primer

DPM-230

DPM Surface Primer, Low Viscosity Epoxy Primer



SINDEC
CHEMICALS

Description

DPM Primer is a two-component epoxy primer with good penetrating properties for use on concrete and polymer modified cementitious screeds.

DPM Primer is designed to improve the adhesion of floor toppings to the substrate. Designed to suppress water pressure, and to function as a damp proof membrane.

Coverage

Coverage varies widely due to the porosity and profile of different substrates.

5 kg Kit - 12 to 20 m²
10kg Kit - 24 to 40 m²

Recommended: 2 Coats to act as a damp proof membrane, each coat will be pigmented differently to help identify the 2 priming coats.

* Coverage figures given are theoretical. Practical coverage rates may vary due to wastage factors and the type, condition, profile and porosity of the substrate.

Environmental Conditions

DPM-230 should not be used or applied at temperatures outside of at range of <10°C to >25°C
*temperature control will be required if below this range.

Otherwise, this will effect the cure period, surface finish and strengths. Surface temperature must be at least 3°C above the dew point. Air temperature should be above 5°C and relative humidity at less than 70%,

Maximum application temperature is 40°C. Best conditions are 15°C to 25°C, these conditions should be maintained during all the curing time. Application should be done with plenty of air ventilation.

Features & Benefits

- Low viscosity - penetrates the substrate
- Seals concrete pores - reduces the potential for out gassing and pin holing in resin floor finishes
- Improves the adhesion of toppings to the substrate
- Easy to mix and apply

Mixing

Pour part B into part A, stir and homogeneize both components using a low-speed mixer using paddle mixer for a minimum of 3 minutes @ 300-400 rpm. Transfer mixed resin into a clean new bucket and mix for a 1 further minute.

Product Application

Once mixed the primer should be applied immediately in a thin continuous film. As a Primer, work the primer into the surface using squeegee then roll to avoid pooling. On porous surfaces DPM-230 will be absorbed very quickly, use enough required amount primer to ensure complete surface sealing.

Suitable Substrates

Thoroughly prepared concrete, polymer modified sand and cement screeds, steel, brickwork, block work and timber.

Substrate Requirements

Inadequate preparation will lead to loss of adhesion and failure. In coatings, there is a tendency for the finish to mirror imperfections in the substrate. Grinding, or light vacuum-contained shot-blasting is therefore preferred over planning for these systems.

If in doubt, apply a test area first.

Requirements as follows:

- Flat and Levelled (Product is Self Smoothing).
- Compact and Cohesive (Pull off test must show a minimum resistance of 1,4N/mm²).
- Minimum compressive strength of 25N/mm².
- Even and regular surface.
- Free from cracks and fissures. If any, they must be previously repaired (we recommend using Sindec Epoxy Crack Filler).
- Clean and dry, free of dust, loose particles, oils, organic residues or laitance.

Oil & Grease

Isolated contamination should be removed using an appropriate degreaser, rinsed thoroughly, and allowed to completely dry. A coat of **OT-235** should then be applied (see separate datasheet)

Reapplication

A Second coat is possible as soon as the first one is touch dry and within the following 24 hours.



DPM Epoxy Primer



SINDEC
CHEMICALS

DPM-230

DPM Surface Primer, Low Viscosity Epoxy Primer

Technical Information

PRODUCT INFO BEFORE APPLICATION

	Component A	Component B
Chemical Description	Epoxy	Polyamine Mixture
Physical State	Liquid	Liquid
Packaging Kits		
5kg kit - Components A & B 10kg kit - Components A & B		
Physical State	Liquid	Liquid
Non-volatile content (%) approximate	>95%	98%
Chemical Description	Epoxy	Polyamine Mixture
Colour	Red/Yellow	Slightly Amber
Mixing Ratio	A = 100 by weight	B = 50 by weight
Use Before	12 months after manufacturing date	
Pot Life	Temp (°C)	Pot Life (100 g, min)
	20	25 mins
Storage	Keep between 15°C an 30°C. Component A may crystallize if stored for protracted periods under certain conditions. If this occurs, it can be restored to its original conditions by heating it to 70-80°C and stirring it thoroughly.	
	6	>70
	25	40
	35	25
	Shelf Life 12 Months	

FINAL PRODUCT INFORMATION

Final State	Solid Membrane, Glossy Material
Colour	Colourless
Hardness (Shore)	80D Shore D hardness after 7 day > 23°C

Environmental Conditions

Empty containers must be handled with the same precautions as if they were full. Treat empty containers as hazardous waste, and transfer them to an authorized waste manager. If the containers still have some material left, do not mix with other product before considering the risk of potential dangerous reactions.

Technical Advice

For further information on this or any other Sindec product, please contact our office.

Health & Safety

Before using this product, please ensure that you have received and read the product Safety Data Sheet. Refer to hazard labelling on the product. Wear gloves and avoid contact with skin and eyes.

Additional Information

The information contained in this document, and all further technical advice given is based on our present knowledge and experience. However, it implies no liability or legal responsibility on our part. In particular, no warranty or guarantee of product performance in the legal sense is intended or implied as the conditions of use and the competence of any labour involved in the application are beyond our control.

Properties and coverage rates shown are for guidance purposes only. The user of the product must determine the product's suitability for the intended purpose. We reserve the right to make any changes according to technological progress or further developments.

Products are guaranteed against defective materials and manufacture and are sold subject to our standard terms and conditions of sale, copies which can be obtained upon request.

Sindec Chemicals try to ensure that the information it may give is accurate and is correct, it cannot control over where and how its products are used or applied, or accept any liability either directly or indirectly arising from the use of its products.

Whether or not in accordance with any advice, recommendation, specification or information given by the Sindec Chemicals.

